



## High Temperature Heating Wire Nickel Alloy Cr20Ni30 Bright Nichrome Resistance Wire

Our Product Introduction

for more products please visit us on [victory-alloy.com](http://victory-alloy.com)

### Basic Information

- Place of Origin: China
- Brand Name: Victory
- Certification: CE
- Model Number: Cr20Ni80
- Minimum Order Quantity: 5
- Packaging Details: Spool package with Carton box, Coil package with polybag for Resistance wire
- Delivery Time: 5-21 days
- Payment Terms: L/C, T/T, Western Union, MoneyGram
- Supply Ability: 300 tons per month



### Product Specification

- Material: Nickel, Chromium
- Nickel(Min): 77%
- Resistivity: 1.09+/-0.05
- Tensile Strength: 637MPA
- Elongation: ≥20%
- Application: Heating, Resistivity
- Condition: Hard / Soft
- Surface: Bright, Oxided, Acide
- Delivery Time: 7-20 Days
- Name: Resistance Wire
- Highlight: Cr20Ni80 nichrome wire heating coil,  
Cr10Ni90 nichrome wire heating coil,  
Cr20Ni30 nichrome wire heating element



### More Images



### Product Description

**Nichrome Cr20Ni80 Cr10Ni90 Cr15Ni60 Cr30Ni70 Cr20Ni30 Electric Heating Resistance Wire Coil For Vapes**

#### NiCr Series

Nichrome wire is a highly versatile material that is widely used in various industries due to its unique properties. It is composed of nickel, chromium, and iron, which give it its non-magnetic alloy characteristic. One of the key properties of nichrome wire is its high resistivity, which means that it can resist the flow of electrical current. This makes it an excellent choice for use in electrical devices that require thermal action, such as heat guns and industrial hair dryers.

In addition to its high resistivity, nichrome wire also has excellent ductility after use and weldability. This means that it can be easily shaped and formed into various shapes and sizes, and can be easily welded together to form larger structures. As a result, it is commonly used to manufacture heating elements for laboratory and

Our Product Introduction

industrial electric furnaces, water heating systems, high-value electrical resistors, heating cords, and cables.

Moreover, nichrome wire has good oxidation resistance, which allows it to withstand high temperatures and prevents it from corroding over time. This makes it an ideal choice for use in applications that require high-temperature resistance.

Overall, nichrome wire is a versatile and reliable material that is essential in many industries. Its unique combination of properties makes it an ideal choice for applications that require high-temperature resistance, electrical resistance, and ductility. Nichrome wire has proven to be a highly useful material in various industrial applications, and its importance in the manufacturing industry cannot be overstated.

**Size dimension range:**

**Wire:** 0.01-10mm

**Ribbons:** 0.05\*0.2-2.0\*6.0mm

**Strip:** 0.05\*5.0-5.0\*250mm

**NiCr series:** Cr20Ni80, Cr30Ni70, Cr15Ni60, Cr20Ni35, Cr20Ni30

Performance material		Cr10Ni90	Cr20Ni80	Cr30Ni70	Cr15Ni60	Cr20Ni35
Composición	Ni	90	Rest	Rest	55.0 61.0	34.0 37.0
	Cr	10	20.0 23.0	28.0 31.0	15.0 18.0	18.0 21.0
	Fe		≤1.0	≤1.0	Rest	Rest
Temperatura máxima °C		1300	1200	1250	1150	1100
Punto de fusion °C		1400	1400	1380	1390	1390
Densidad g/cm3		8.7	8.4	8.1	8.2	7.9
Resistividad μΩ·m,20°C		0.76±0.05	1.09±0.05	1.18±0.05	1.12±0.05	1.00±0.05
Alargamiento a la ruptura		≥20	≥20	≥20	≥20	≥20
Calor específico J/g.°C			0.44	0.461	0.494	0.5
Conductividad térmica KJ/m.h°C			60.3	45.2	45.2	43.8
Coeficiente de expansión de líneas α×10-6/(20 1000°C)			18	17	17	19
Estructura micrográfica			Austenite	Austenite	Austenite	Austenite
Propiedades magnéticas			Nonmagnetic	Nonmagnetic	Nonmagnetic	Weak magnetic

Form	Specification	
Wire	Diameter=0.025mm~8mm	
Flat wire	Width=0.40~6.0mm	Thick=0.03~0.50mm
Strip	width=8~250mm	Thick=0.05~3.0mm
Bar	Diameter=8~100mm	Long=50~1000

NiCr 80/20 is suitable for heating elements used for temperatures upto 1200°C. This is used for electrical cooking equipment, precision resistors. Oxidized wires of these alloys display better insulation properties.

NiCr 70/30 is suitable for heating elements used for temperatures upto 1230°C for industrial furnaces which have alternating oxidizing, or reducing atmosphere. This alloy has excellent corrosion resistance and long life in air and controlled atmospheres.

NiCr 60/15 is suitable for heating elements used for temperatures upto 1150°C. This is used for electrically heated equipment, high resistance and potentiometer resistors.

NiCr 30/20 is suitable for heating elements used for temperatures upto 1050°C. In spite of relatively high Fe content, these alloys are resistant to oxidation and chemical corrosion. They are used for making heating elements of cooking equipment, heating cords and cables.

 victory-alloy.com

NO.32 West Taihu Road, Xinbei District, Changzhou, Jiangsu